



TC-5389

ELECTRICAL RESEARCH AND DEVELOPMENT ASSOCIATION

(Accredited by the National Accreditation Board for Testing and Calibration Laboratories, Govt. of India)

ERDA Road, Makarpura Industrial Estate, Vadodara-390 010, India.

EPABX : +91 (0265) 2642942, 2642964, 2642377, 3043128 / 29 / 30 / 31 / 33

Fax : +91 (0265) 2638382

E-mail : erda@erda.org



Web : http://www.erda.org



ULR No. TC538924000028487F

Discipline: Electrical Testing

Group: Insulating Materials & Insulators

TEST REPORT No. RP-2425-027053		DATE OF ISSUE 10-12-2024	SHEET 2 OF 2	
Sr. No.	Particular of Tests & Cl. No.	Requirements as per specification	Obtained value	Remarks
1.	Volume resistivity, Ω .cm (in air at 26 °C) Cl. No. 12.2 Applied Voltage: 500Vdc Electrification Time: 60 seconds Average of measured thickness: 0.58mm	---	Average 2.18×10^{15}	---
 <p>Photograph of sample in as received condition</p>				
<p>CHECKED BY </p>				

*****End of Test Report*****



TC 3728016